




2581-4575

International Journal For Recent Developments in Science & Technology



A Peer Reviewed Research Journal



DETAIL STUDY ON DIELECTRIC POLYMER COMPOSITES WITH HIGH THERMAL CONDUCTIVITY

MAREPALLY SRIDHAR DR.V.ASHOK KUMAR, K.UPENDER

PG Scholar Department of Mechanical Engineering, Mother Theresa College of Engineering & Technology

Associate professor & HOD Department of Mechanical Engineering, Mother Theresa College of Engineering & Technology

Assistant Professor Department of Mechanical Engineering, Mother Theresa College of Engineering & Technology

ABSTRACT : There has been a growing interest in utilizing natural fibers as reinforcement in polymer composite for making low cost construction materials in recent years. The present paper surveys the research work published in fiber reinforced polymer composite materials with reference to electrical properties such as volume resistivity, dielectric constant, dielectric dissipation factor and dielectric loss factor. Such studies are important because fibrous reinforcements in polymer matrices lead to composite materials with good mechanical properties and electrical properties. The electrical properties such as dielectric constant, dielectric dissipation factor and dielectric loss factor were determined with respect to temperature and frequency. The studies showed that dielectric constant and dielectric dissipation decreased with frequency and increased with temperature, where as the dielectric loss factor decreased with the increase of frequency at fixed temperature and increased with temperature at lower frequencies. It is also observed that the dielectric loss factor decrease with chemical treatment.

Keywords : Natural fiber composites, electrical properties.

INTRODUCTION

In recent years, polymer composites containing natural fibers have obtained considerable attention. The interest in the natural fiber reinforced polymer composite arises rapidly due to the high performance in mechanical properties, significant processing advantages, low cost and low density [1,2]. Natural fibers are renewable, cheaper, pose no health hazards and finally provide a solution to environmental

pollution by finding new uses for waste materials. Furthermore, natural fiber reinforced polymer composite form a new class of materials which seem to have good potential in future as a substitute for scarce wood and wood based materials in structural applications. Many plant fibers have found applications as a resource for industrial materials [3,4]. In addition to cellulose, plant fibers contain different natural




2581-4575

International Journal For Recent Developments in Science & Technology



A Peer Reviewed Research Journal



substances. The most important of these is lignin. The different cells of hard plant fibers are bonded together by lignin, acting as cementing materials. The lignin content of the plant fibers influences its structure, properties and morphology. The composites mainly consist of cellulose fibrils embedded in lignin matrix. These fiber exhibits high electrical resistance. It can be expected that when these fibers are incorporated into low modulus polymer matrix, they would yield materials with better properties suitable for various applications. The properties of natural fiber composites were influenced by fiber loading, dispersion and fiber to matrix adhesion [5-10]. The uses of composites as dielectric are becoming more popular, therefore the electrical properties of natural fiber reinforced polymer composites are very important. The electrical properties such as volume resistivity, dielectric strength of some natural fibers and composites have been studied [7,8].

Saxena et al. have studied the variation of thermal conductivity and thermal diffusivity of banana fiber reinforced polyester composite caused by addition of glass fiber [22]. They observed that the thermal conductivity of composites increased when compared to matrix. However, the thermal conductivity of the composites with increased percentage of glass fiber decreases in comparison to composite of pure banana fiber. Mai et al. have studied the effect of fiber length and fiber orientation angle on the thermal conductivity of short carbon fiber reinforced composite materials [23]. It is observed that the thermal conductivity of

the composite increased with fiber length but decreases with fiber orientation angle with respect to the measured direction. The polymeric interfaces act as charge carrier generation sites [24]. So it becomes essential to study the effect of interfaces on the charge carrier generation, transport and storage in polymeric system. The physical structure of polymer composites in the solid or viscoelectric state is of great importance in determining the dielectric behavior [25]. The dielectric properties of polymer composite materials have been studied with a view to modify the properties of polymer system for practical applications. The inorganic insulators and dielectrics have been largely replaced by polymers on account of their unique ability for specific needs. Epoxides and polyesters have been used in electronics as insulators, dielectrics substrates, potting compounds, embedding materials and conformal coating [26]. Fiber reinforced composite materials have wide range of applications in aircraft automobile, chemical, medical and electrical industries. In the electrical or electronics industry, these composite materials are used for making panel, switches, and insulators.

Electrical property determination

The capacitance, resistance, dissipation factor and dielectric loss factor have been measured directly by using LCR meter by varying frequencies at room temperature. The square samples of thickness 3mm, length 10 mm and breadth 10 mm have been used for study. The test samples were fixed between two electrodes.

The volume resistivity (\square) :




2581-4575

International Journal For Recent Developments in Science & Technology



A Peer Reviewed Research Journal



It can be calculated from the resistance using following equation,

$$\rho = RA/t$$

where,

A - area of cross-section of the sample

R - resistance

t - thickness of the sample.

The dielectric constant (ϵ^1) :

It can be calculated from the capacitance using equation

$$\epsilon^1 = ct/\epsilon_0 A$$

where,

ϵ_0 - permittivity of air ($8.85 \times 10^{-12} \text{ Fm}^{-1}$)

C - capacitance with dielectric

A - area of cross-section of the sample

t - thickness of the sample.

The dielectric dissipation factor ($\tan \delta$) :

It can be determined as follow

$$\tan(\delta) = \epsilon^{\text{II}}/\epsilon^1$$

where,

ϵ^{II} - the dielectric loss.

The dielectric loss factor (ϵ^{II}) :

It can be determined as follow

$$\epsilon^{\text{II}} = C/C_0\omega$$

DISCUSSION

The resistivity of fiber reinforced composites depend on the moisture content, crystalline and amorphous component present, presence of impurities, chemical composition, cellular structure, microfibrillar angle etc. The shapes of reinforcement determine the interparticle contact, which affect the conductivity of the system. Fibers and flakes having elongated shapes affect the electrical conductivity [27]. The moisture content in fibers increased the conductivity [16]. The hydrophilicity of cellulose fiber is responsible for greater conductivity of the composite. In polymeric materials most of the current flow through the crystalline regions and non crystalline region allows current to pass through it mainly when moisture is present [15]. The

hydroxyl groups in the hydrophilic fiber can absorb moisture and hence the presence of the natural fiber increases the conductivity of the resin. It has been found that heat treatment increased the resistivity of the composites as heat treated fiber reinforced composites have lower moisture content than untreated fiber reinforced composites.

It has been observed that dielectric loss factor decreased with the increase of frequency at fixed temperature. The loss peaks were observed at about 1 kHz at high temperature in composite materials, which may be due to the temperature glass transition in polyester [33]. In the composite materials the absorbed moisture at the fiber resin interface acts as a plasticizing agent for the polymer, which increases the mobility of the polymer chain and hence brings the loss peak due to temperature glass transition of polyester at higher frequency value [34]. Joseph et al. have observed that in banana fiber composites, at low frequencies, dielectric loss factor increased with increase in fiber loading [21]. They observed that at high frequency, a reverse behavior occurs and the values come closer. This was due to the polarization of the fibers at low frequencies, which was absent at higher frequencies. The dielectric loss factor increased with temperature, particularly at lower frequencies at which dielectric loss due to chain motion of polymer is more effective due to glass transition temperature of the polymer. At higher frequencies, the dielectric loss factor is low and remained more or less constant with increasing temperature because the orientation




2581-4575

International Journal For Recent Developments in Science & Technology



A Peer Reviewed Research Journal



polarization due to chain motion of polymer can not keep phase with the rapidly oscillating electric field [35].

CONCLUSION

The electric properties of natural fiber reinforced composites were reviewed. The electrical properties of natural fiber reinforced polymer composites are very important. Due to their unique the inorganic insulators and dielectrics have been replaced by polymers for specific needs. Epoxides and polyesters have been used in electronics as insulators, dielectrics substrates, potting compounds, embedding materials and conformal coating. The moisture content in fibers increases conductivity of the composites. . It has been found that heat treatment increased the resistivity of the composites as heat treated fiber reinforced composites. The increase of dielectric constant with temperature is due to greater freedom of movement of dipole molecular chain at high temperature. It has been observed that dielectric dissipation factor increased with temperature and decreased with frequency. It has been further observed that dielectric loss decreased with the increase of frequency at fixed temperature. It can be concluded that with systematic and persistent research there will be good scope and better future for polymer reinforced composites for suitable electrical boards etc.

REFERENCES

[1] Satyanarayana, K.G., Sukumaran, K., Mukherjee, P.S., Pavithran, C. and Pillai, S.G.K., International conference on low cost housing for developing countries (Rookree, 1984), pp. 171-181.

[2] Satyanarayana, K.G., Pai, B.C., Sukumaran, K, and Pillai, S.G.K., Lignocellulosic fiber reinforced polymer composites (New York, Marcel Decker, Vol.1, p. 339, (1990).

[3] Thomas, S. and Udo, G., Ligno. Plast. Compos., 181, (1997).

[4] Rowell, R.M., Sanadi, A.R., Caulfield, D.F. and Jacobson, R.E., Ligno. Plast. Compos., 21: (1997).

[5] Bledzki, A.K., Gassan J. Compos., 24: 221(1999).

[6] Kulkarni, A.G., Satyanarayana, K.G. and Rohatgi, P.K., J. Mater. Sci., 18: 2290(1983).

[7] Paul, A., Joseph, K. and Sabu, T., Compos. Sci. Technol., 67(1997).

[8] Reid, J.D., Lawrence, W.H. and Buck, R.P., J. Appl. Polym. Sci., 30: 1771(1986).

[9] Chand, N., Verma, S. and Khazanchi, A.C., J. Mater. Sci. Lett., 8: 1307(1989).

[10] Yang, G.C., Zery, H.M., Jain, L.L. and Zhang, W.B., Acta Scientir. Natur. Uni. Syny., 35: 55(1997).

[11] Morsli, M., Bonnet, A., Samir, F. and Lefrent, S., J. Appl. Poly. Sci., 61: 231(1996).

[12] Wu, S.L. and Tung, I.C., Poym. Compos., 16: 3(1995).

[13] Jayamol, G., Bhagwan, S.S., and Thomas, S., J. Polm. Eng., 17: 5(1997).

[14] Chand, N. and Jain, D., Compos. A, 36: 594(2005).

[15] Paul, A. and Thomas, S., J. Appl. Poly. Sci., 63: 247(1997).




2581-4575

International Journal For Recent Developments in Science & Technology



A Peer Reviewed Research Journal



- [16] Kulkarni, A.G., Satyanarayana, K.G. and Rohatgi, P.K., *J. Mater. Sci.*, 16: 1719(1981).
- [17] Paul, A., Joseph, K. and Thomas, S., *Compos. Sci. Technol.*, 57: 67(1997).
- [18] Paul, A., Thomas, S. and Pavitharan, C., *J. Appl. Polm. Sci.*, 63: 247(1997).
- [19] Yan, L., Yiu, W.M. and Lin, Y.E., *Compos. Sci. Technol.*, 60: 2037(2000).
- [20] Fraga, A., Frulloni, E., Osa, O.D.L., Kenny, J.M. and Vazquez, A., *Polym. Test*, 25: 181(2006).
- [21] Joseph, S., and Thomas, S., *J. Appl. Poly. Sci.*, 109: 256(2008).
- [22] Agarwal, R., Saxena, N.S., Sharma, K.B., Thomas, S. and Pothan, L.A., *Ind. J. Pure Appl. Phys.*, 41: 448(2003).
- [23] Fu, S.Y. and Mai, Y.W., *J. Appl. Polym Sci.*, 88: 1497(2003).
- [24] Tripathi, A.K. and Pillai, P.K.C., *Proceeding of the 5th International Symposium on Electrets, Heidelber (IEEE, New York, 1985).*
- [25] Aras, L. and Baysal, M., *J. Polym Sci. Polym. Phys. Edn.*, 22: 1453(1984).
- [26] Singh, D.B., Kumar, A., Tayal, V.P. and Sanyal, B., *J. Mater. Sci.*, 23: 523(1988).
- [27] Blythe, A.R., *Electrical properties of polymer,* Cambridge University Press Cambridge, London, (1979).
- [28] Chand, N. and Jain, D., *Compos.*, 36: 194(2005).
- [29] Smyth, C.P., *Dielectric behavior and structure,* McGraw Hill (Oxford, 1956, pp. 53)
- [30] Frohlick, H., *Theory of Dielectrics,* Oxford University Press (Oxford, 1956, pp. 13).
- [31] Jayamol, G. and Bhagwan, S.S., Thomas, S., *J. Polym. Eng. 17: 5(1997).*
- [32] Sreekala, M.S., Ph.D. Thesis, Mahatma Gandhi University, Kottayam, Kerla, India, 2000.
- [33] Mateen, A., PhD Thesis, Centre for Solid State Physics, University of Punjab (Lahore, Pakistan, 1983).
- [34] Polac, E., *Epolac Technical data Bulletin,* Nippon Shokubai Kagaku (Kogyo, Co. Ltd, Japan, 1985).
- [35] Akram, M., Javed, A. and Rizvi, T.Z., *Turk J Phys.*, 29: 355(2005).